

# CT-DP1110

## CINTA AUTOADHESIVA DOBLE CARA

### CARACTERÍSTICAS:

- Adhesivo acrílico extremo
- Alta adhesión a la superficie
- Fuerte adhesión inicial
- Resistencia al envejecimiento y a la temperatura

### Aplicación típica:

Para sellar superficies basadas en papel y películas plásticas



CT-DP1110			TEST METHOD
Construcción	Paper Tissue Carrier // Acrylic adhesive// Double side silicone paper liner		
PROPERTIES	Metric	English	
Espesor Total	110 Micras	4.3 mil	PSTS-33 / ASTM D 3652
Adhesión a la superficie	18 N/25mm	65 Oz/pulgadas	PSTC-1 / ASTM D 3330
Rollo base (11 mm de diametro)	10 cm	4 pulgadas	PSTC-6 / ASTM D 3121
Resistencia a la tracción	40 N/25 mm	9 Lb/pulgadas	PSTC-31 / ASTM D 3759
Estiramiento	3.5%	3.5%	PSTC-31 / ASTM D 3759
Temperatura de Servicio	-20 +100 C	-4 + 212 °F	-----
Core I.D.	76mm	3"	
Ancho de Rollo	50mm (2"), 60mm, 75mm (3")		
Largo de Rollo	30m (100'), 45m (50 yards), 50m, 100m		

- The data above are typical results from tests conducted on samples taken from production runs and may be updated without notice. Typical values are not intended to be used for specification development.
- The product should be stored in the original packaging material at 20 +/- 5 C and 40-60% relative humidity and protected from direct sunlight, heat and moisture. Shelf life: One year when stored at the conditions described above.
- The surface to which the tape is applied must be clean, dry, free of grease and oil and other contaminants and deposits. Recommended temperature of application: 50 - 105 °F (10 - 40 °C).
- The user is responsible for determining whether the product is fit for a particular surface and suitable for user's application. The user should make necessary tests and trial-application of the tape to confirm suitability for user's special purpose and method of application.
- Self adhesive tapes are designed for sealing applications only. In the instance when the sides of the joint are subject to mechanical stress, both sides should be securely positioned using appropriate fasteners or hangers prior to the self adhesive tapes application.
- Calem Technology warranty that the product is free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment, Calem Technology shall, upon notification thereof and substantiation that the product have been stored and applied in accordance with the above requirements, at Calem Technology discretion, replace or credit the product's purchasing price equivalent.
- Limitation of liability. Calem Technology Inc. and seller of CT Tape products will not be liable for any loss or damage arising from the CT Tape product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Distribuidores Autorizados

Norte 94, #4534 Nueva Tenochtitlan  
07890 Gustavo A. Madero, CDMX

✉ info@solucionesenaislamiento.com

☎ (55) 9129-8722 📞 (55) 7990-6920

● www.solucionesenaislamiento.com